



PRODUCT DATA

IROGRAN A 85 P 4394

Thermoplastic Polyurethane

INTRODUCTION

IROGRAN A85P 4394 is a high performance polyether based thermoplastic polyurethane intended for extrusion and injection moulding applications.

IROGRAN A85P 4394 is part of the HUNTSMAN technical extrusion product range and offers a specially designed, flexible material with a broad processing window particularly suitable for the preparation of tubing, cable jacketing and technical mouldings.

PERFORMANCE FEATURES

- High tensile strength
- Excellent wear performance
- Excellent hydrolysis & microbial resistance
- Good low temperature flexibility

Table 1: Typical Physical Properties

Physical Properties						
Property	Key	DIN	Unit	Value	ASTM	Unit Value
Hardness	M	53505	Shore A	85	D-2240	Shore A 85
Hardness	M	53505	Shore D	36	D-2240	Shore D 36
Tensile Strength	M	53504	MPa	45	D-412	psi 5500
Elongation @ break	M	53504	%	640	D-412	% 610
100% Modulus	M	53504	MPa	6.0	D-412	psi 940
300% Modulus	M	53504	MPa	12.0	D-412	psi 1690
Tear Resistance	M	53515	N/mm	70	D-624	pli 400
Abrasion	M	53516	mm ³	35	D-395	
Compression Set 24hrs @ 23°C	M	53517	%	25	D-395	% 25
Compression Set 24hrs @ 70°C	M	53517	%	45	D-395	% 45
Mold Shrinkage	M		cm/cm	0.006	D-955	in/in 0.006
Specific Gravity	M	53479	g/cm ³	1.12	D-792	1.12
TMA Low	E	Huntsman	°C	165	Huntsman	°F 329
TMA High	E	Huntsman	°C	195	Huntsman	°F 383

E= 0.025" extruded film cut to ASTM requirements

M = Injection moulded parts to meet DIN & ASTM requirements. Parts tempered for 20hrs @ 100°C prior to testing



PRODUCT DATA

IROGRAN A 85 P 4394

Thermoplastic Polyurethane

POLYMER SELECTION

Before selecting this product it is necessary that the user ensures the product performance will meet all operational and end use requirements. Having satisfied these requirements, should changes be contemplated in method of application, materials, service conditions or any other change that could affect the ultimate performance of the end product, then further tests and trials should be carried out. For assistance with particular problems and applications, please contact the IROGRAN TPU Technical Service Department.

HEALTH & SAFETY ADVICE

Before undertaking any trials with this product it is essential that all personnel are aware of the necessary precautions that must be taken. These are detailed in the relevant Safety Data Sheet, which will be provided by HUNTSMAN.

SUPPLY & STORAGE

IROGRAN A 85 P 4394 is supplied in the form of pellets. Standard packaging is a 25 kg moisture guarded sack, 40 per pallet and shrink-wrapped. Additionally the product may be supplied in fiber drums or cardboard gaylord boxes.

IROGRAN A 85 P 4394 has a minimum expected shelf life of 12 months from the date of shipment when stored in a cool and dry place in the manufacturer's original packaging.

PHYSICAL FORM

Type: Pellet
Bulk Density: 673 kg/m³ [42 lb/ft³]

MATERIAL PREPARATION

IROGRAN TPU grades are supplied pre-dried in moisture guarded sacks. To ensure trouble free processing it is preferable to dry IROGRAN TPU. The recommended drying conditions are:

- 3 hours at 100-110°C in circulating air
- 3 hours at 80-90°C in dehumidified air
- Dew point: -22°F / -30°C

For further advice on the use of additives during the processing please contact the IROGRAN TPU Technical Service Department.

PROCESSING PARAMETERS

Table 2: Typical Processing Parameters

Processable by: Extrusion
Injection Moulding
Melt Volume rate
[190°C/21.6 kg] 65 cm³/10 min

Extrusion

Temperature Profile	°C	°F
Feed Zone	25-40	77-104
Barrel	160-200	320-392
Adapter	175-200	347-392
Die Head	175-205	347-401

Injection Moulding

Temperature Profile	°C	°F
Heating Zone	170-210	338-410
Nozzle	200-210	392-410
Melt Temperature	190-205	374-401
Mould Temperature	20-70	68-158

The address of your nearest technical centre is:

USA

Huntsman
52 Kendall Pond Road
Derry, NH 03038 USA
Tel: +1 603 421 3500
Fax: +1 603 421 3510

EUROPE

Huntsman
Hafenringstrasse 1
49090 Osnabrück Germany
Tel: +49 541 9141 360
Fax: +49 541 9141 395

ASIA

Huntsman
No. 19, Industrial Third Road
Kuan Yin, Taoyuan Country, Taiwan, R.O.C
Tel: +886 348 38616
Fax: +886 348 39324

Web: www.huntsman.com/tpu

While the information and recommendations in this publication are, to the best of our knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. NOTHING IN THIS PUBLICATION IS TO BE CONSTRUED AS RECOMMENDING THE INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT, AND NO LIABILITY ARISING FROM ANY SUCH INFRINGEMENT IS ASSUMED. NOTHING IN THIS PUBLICATION IS TO BE VIEWED AS A LICENCE UNDER ANY INTELLECTUAL PROPERTY RIGHT. Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of Huntsman International LLC or of its affiliated companies. Huntsman Polyurethanes is an international business unit of Huntsman International LLC. Huntsman Polyurethanes trades through Huntsman affiliated companies in different countries such as Huntsman International LLC in the USA and Huntsman Holland BV in Western Europe.

IROGRAN is a registered trademark of Huntsman International LLC in one or more countries, but not all countries.
Copyright © Huntsman International LLC 2003. All rights reserved.