

Product Data Sheet

Eastman Spectar™ copolyester 14471

Application/Uses

- Displays and Fixtures
- Indoor signage
- POP (Point of Purchase)
- Shelving systems

Key Attributes

- Easy to print and decorate
- Excellent clarity
- Excellent thermoforming characteristics
- Good chemical resistance
- Odorless
- Outstanding impact resistance
- Outstanding toughness allows downgauging
- Resists chipping and cracking
- Versatile - easy to fabricate

Product Description

Eastman Spectar™ copolyester (PETG) extrudes into plastic sheet that is sparkling clear, tough, chemically resistant, odor-free, versatile, easy to work with and affordable. Its toughness allows fabricators to use thinner-gauge sheet than with other common materials, resulting in lower material costs. Yet it can be extruded into sheets as thick as 12 mm (1/2 in.). It extrudes at a low temperature and will not crystallize or develop a crystalline haze. Cleaning solutions will not turn Eastman Spectar™ copolyester white. It is easy to fabricate, allowing greater design freedom. It can be laser cut, routed, welded, drilled, die-punched, bent hot or cold, or joined by screws, rivets, or bolts. It can also be cut on conventional table, band, or radial-arm saws with blades commonly used for plastic. Spectar™ copolyester can be vacuum-formed at lower temperatures than other plastics without predrying the sheet. Eastman Spectar™ copolyester can be finished easily. Its edges can be polished by using commercial edge-finishing equipment, sanding, solvents, flame-polishing or buffing. It forms clear, strong bonds with commercially available cements and solvents. It accepts screen-printing, painting, and hot-stamping easily. Surface scratches or scuff marks can be removed using a common heat gun.

Sheet made from Eastman Spectar™ copolyester (PETG) is available from plastic sheet distributors throughout North America, Canada, Europe, Asia, and Latin America.

This product has been GREENGUARD INDOOR AIR QUALITY CERTIFIED®. GREENGUARD Certification recognizes Eastman for manufacturing products with low chemical and particle emissions for better indoor environments. For more information about GEI and to obtain printable certificates for Eastman™ Copolyesters, visit www.greenguard.org. Choose Eastman Chemical Company under the Manufacturer category and click search to display a list of our products.

This product is certified to NSF/ANSI Standard 51 for Food Equipment Materials.

This product has been CRADLE TO CRADLE CERTIFIED^{cm} Silver.

The CRADLE TO CRADLE CERTIFIED^{cm} Mark is a registered certification mark used under license through McDonough Braungart Design Chemistry (MBDC). MBDC is a global sustainability consulting and product certification firm. The CRADLE TO CRADLE® framework moves beyond the traditional goal of reducing the negative impacts of commerce ('eco-efficiency'), to a new paradigm of increasing its positive impacts ('eco-effectiveness'). At its core, Cradle to Cradle design perceives the safe and productive processes of nature's 'biological metabolism' as a

model for developing a 'technical metabolism' flow of industrial materials. Product components can be designed for continuous recovery and reutilization as biological and technical nutrients within these metabolisms. For more information about MBDC and to obtain printable certificates for Eastman Copolyesters, visit www.mbdc.com. Choose Eastman Chemical Company under Company Name in C2C Certified products to display a list of our products.

Typical Properties

Property ^a	Test ^b Method	Typical Value, Units ^c
Thickness of Sheet Tested		3 mm
General Properties (ASTM Method)		
Density	D 1505	1.27 g/cm ³
Water Absorption, 24 h immersion	D 570	0.2%
Mechanical Properties (ASTM Method)		
Tensile Stress @ Yield	D 638	53 MPa (7700 psi)
Tensile Stress @ Break	D 638	26 MPa (3800 psi)
Elongation @ Yield	D 638	4.8%
Elongation @ Break	D 638	50%
Tensile Modulus	D 638	2200 MPa (3.2 x 10 ⁵ psi)
Flexural Modulus	D 790	2100 MPa (3.1 x 10 ⁵ psi)
Flexural Strength	D 790	77 MPa (11200 psi)
Rockwell Hardness, R Scale	D 785	115
Izod Impact Strength, Notched		
@ 23°C (73°F)	D 256	88 J/m (1.7 ft·lbf/in.)
@ 0°C (32°F)	D 256	66 J/m (1.2 ft·lbf/in.)
@ -30°C (-22°F)	D 256	39 J/m (0.7 ft·lbf/in.)
Impact Strength, Unnotched		
@ 23°C (73°F)	D 4812	NB
@ 0°C (32°F)	D 4812	NB
@ -30°C (-22°F)	D 4812	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C (73°F)	D 3763	33 J (24 ft·lbf)
@ 0°C (32°F)	D 3763	40 J (30 ft·lbf)
@ -10°C (14°F)	D 3763	42 J (31 ft·lbf)
@ -20°C (-4°F)	D 3763	43 J (32 ft·lbf)
@ -30°C (-22°F)	D 3763	47 J (34 ft·lbf)
Thermal Properties (ASTM Method)		
Deflection Temperature		
@ 0.455 MPa (66 psi)	D 648	74°C (164°F)

@ 1.82 MPa (264 psi)	D 648	70°C (157°F)
Vicat Softening Temperature @ 1 kg load	D 1525	83°C (181°F)
Oxygen Index ^d	D 2863	26%
Coefficient of Linear Thermal Expansion ^e	D 696	7 x 10 ⁻⁵ /°C (mm/mm·°C) (4 x 10 ⁻⁵ /°F (in./in.·°F))

Optical Properties (ASTM Method)		
Haze	D 1003	<1%
Regular Transmittance	D 1003	89%
Total Transmittance	D 1003	91%
Gloss @ 60°	D 523	159
Color, b* CIELAB, Illuminant D6500, 10° Observer	E 308	<1
Yellowness Index CIELAB, Illuminant D6500, 10° Observer	D 1925	<1.5
Refractive Index, n _D	D 542	1.57

Electrical Properties (ASTM Method)		
Dielectric Constant		
1 kHz	D 150	2.6
1 MHz	D 150	2.4
Dissipation Factor		
1 kHz	D 150	0.005
1 MHz	D 150	0.02
Arc Resistance	D 495	158 sec
Volume Resistivity	D 257	10 ¹⁵ ohm·cm
Surface Resistivity	D 257	10 ¹⁶ ohms/square
Dielectric Strength, Short Time, 500 V/sec rate-of-rise	D 149	16.1 kV/mm (410 V/mil)

General Properties (ISO Method)		
Density	ISO 1183	1270 kg/m ³
Water Absorption, 24 h immersion	ISO 62	0.2%

Mechanical Properties (ISO Method)		
Tensile Stress @ Yield	ISO 527	53 MPa
Tensile Stress @ Break	ISO 527	26 MPa
Elongation @ Yield	ISO 527	4.7%
Elongation @ Break	ISO 527	40%
Tensile Modulus	ISO 527	2200 MPa
Flexural Modulus	ISO 178	2100 MPa
Flexural Strength	ISO 178	69 MPa
Izod Impact Strength, Notched		

@ 23°C	ISO 180	11.5 kJ/m ²
@ 0°C	ISO 180	6.1 kJ/m ²
@ -30°C	ISO 180	4.4 kJ/m ²
Charpy Impact Strength, Notched		
@ 23°C	ISO 179	10 kJ/m ²
@ 0°C	ISO 179	4.2 kJ/m ²
@ -30°C	ISO 179	3.3 kJ/m ²
Charpy Impact Strength, Unnotched		
@ 23°C	ISO 179	NB
@ 0°C	ISO 179	NB
@ -40°C	ISO 179	NB
Impact Resistance (Puncture), Energy @ Max. Load		
@ 23°C	ISO 6603-2	59 J
@ 0°C	ISO 6603-2	61 J
@ -10°C	ISO 6603-2	70 J
@ -20°C	ISO 6603-2	73 J
@ -30°C	ISO 6603-2	74 J

Thermal Properties (ISO Method)

Deflection Temperature		
@ 0.45 MPa	ISO 75	72°C
@ 1.80 MPa	ISO 75	68°C
Vicat Softening Temperature		
@ 1 kg load	ISO 306	83°C
@ 5 kg load	ISO 306	78°C

Thermal Properties (Flammability)

UL Flammability Classification	UL 94	94V-2
Flammability/France	NFP 92-501	M2
Flammability/Germany ^f	DIN 4102 - Part 1	B1
Flammability/Great Britain ^f	BS 476 - Part 7	1Y

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

^d Dripping and warpage of samples during testing can cause erratic test results.

^e -30°C to 23°C

^f Indicative testing only. Only 1 or 2 samples were tested to the specified test method, and the full requirements of the standards were not met. The results do not indicate compliance with a regulatory requirement.

General

Specimens were machined from extruded sheeting with a thickness as indicated. For Flammability/Great Britain, a suffix Y is added to the classification if any softening and/or other behaviour that may affect flame spread occurs.

Comments

Properties reported here are typical of average lots. Eastman makes no representation that the material in any particular shipment will conform exactly to the values given.

Eastman and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

24-Dec-2008 11:58:18 AM